



## John Neal Bookseller Paper Comparison Chart

Use this chart to get a rough weight comparison between papers.  
 We've included standard copy and inkjet paper for a point of reference.  
 Our fine papers use gsm (grams per square meter) as the measure of weight.  
 This measures weight only, not thickness. For example, some 20lb bonds  
 are thicker than others.

	gsm	lb bond	lb text
Standard 20lb bond Copy Paper	74	20	50
Standard 24lb bond Inkjet Paper	89	24	60
Zerkall Book White	100	27	68
Canson Ingres	100	27	68
German Ingres	100	27	68
Niddeggen	120	34	82
Frankfurt	120	34	82
Arches Text Wove	120	34	82
Arches Text Laid	120	34	82
Burga	130	37	88
Pergamenata	160	46	109
Arches HP, CP 90lb	185	50	126
Pergamenata Heavy	230	62	156
Stonehenge	250	68	170
Arches Cover Black	250	68	170
Arches HP, CP 140lb	300	81	204